



(11) **EP 2 228 352 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
15.09.2010 Bulletin 2010/37

(51) Int Cl.:
C04B 28/02 (2006.01) **C04B 28/10 (2006.01)**

(21) Application number: **09461502.8**

(22) Date of filing: **04.03.2009**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK TR
Designated Extension States:
AL BA RS

(74) Representative: **Fietko-Basa, Sylwia**
Kancelaria Patentowa
Grazyna Basa
Ul. Jagiellonska 59
25-734 Kielce (PL)

(71) Applicant: **ALPOL Gips Sp. z o.o.**
26-200 Konskie (PL)

Remarks:
Amended claims in accordance with Rule 137(2) EPC.

(72) Inventor: **Bak, Lukasz**
27-400, Ostrowiec Swietokrzyski (PL)

(54) **Mortar especially for shaped clinker bricks**

(57) Mortar designed especially for shaped clinker bricks comprised of the dry mixture of cement, fillers, chemical additives and requiring addition of water only, is **characterised in that** it contains from 15 to 28% of cement by weight, from 50 to 68% of quartz sand of grain size from 0.1 to 1.25 mm by weight, from 2 to 10% of quartz sand of grain size from 0.1 to 0.2 mm by weight, from 4 to 10% of limestone flour of grain size of up to 0.5 mm by weight, from 1 to 5% of quartz flour of grain size of up to 0.25 mm by weight, modified cellulose ether from 0.05 to 0.3% by weight, redispersible powder from 0.5 to

1.0% by weight, aerating additive in the amount from 0.01 to 0.02% by weight, favourably organic and non-organic pigments in the amount from 0.1 to 4% by weight, additive of nanometric size favourably belonging to the group of silicates in the amount from 0.05 to 0.5% by weight, water-proofing agent in the form of silicone, powder of nanometric size in capsules in wax envelopes in the amount from 0.2 to 0.5% by weight, and biocide favourably in the amount from 0.03 to 0.3% by weight

EP 2 228 352 A1

Description

[0001] The subject of the invention comprises mortar for shaped clinker bricks, used to lay and joint wall elements with the use of shaped clinker bricks and elevation elements available in the market. The invention is primarily meant for construction industry.

[0002] The already known mortars preventing occurrence of patches of efflorescence contained pozzolanic additives, in particular fly-ash, silica fume or trass flour and/or hydraulic additive, especially ground, granulated blast furnace slag that bind calcium hydroxide and/or aerating, hydrophobic additives and/or starch ethers.

[0003] Another mortar is also known that contains additives of nanometric size, in particular those that belong to the group of silicates.

[0004] The purpose of the invention is to develop a mortar that shall be resistant to migrations of dissolved salts and thus resistant to occurrence of patches of efflorescence and to fungal attacks. Migrating salts can come both from the ingredients of mortars, clinker tiles made of improper raw materials as well as they can be a product of atmospheric influence on mortars.

[0005] Mortar especially for shaped clinker bricks comprised of the dry mixture of cement, fillers, chemical additives and requiring addition of water only, according to the invention is **characterised in that** it contains from 15 to 28% of cement by weight, from 50 to 68% of quartz sand of grain size from 0.1 to 1.25 mm by weight, from 2 to 10% of quartz sand of grain size from 0.1 to 0.2 mm by weight, from 4 to 10% of limestone flour of grain size of up to 0.5 mm by weight, from 1 to 5% of quartz flour of grain size of up to 0.25 mm by weight, from 0.05 to 0.3% of modified cellulose ether by weight, from 0.5 to 1.0% of redispersible powder by weight, from 0.01 to 0.02% of aerating additive by weight, favourably from 0.1 to 4% of organic and non-organic pigments by weight, 0.05 to 0.5% of additive of nanometric size favourably belonging to the group of silicates by weight, from 0.2 to 0.5% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, and favourably from 0.03 to 0.3% of biocide by weight.

[0006] The mortar according to the invention favourably also contains additives of pozzolanic nature, especially fly-ash or silica fume or trass flour in the amount from 0.5 to 1.0%, and/or hydraulic additive especially ground, granulated blast furnace slag in the amount from 1.0 to 5.0%, and/or starch ethers in the amount from 0.01 to 0.02%, and/or flexibility-improving additives, especially added in the form of ready resin dispersion of acrylic co-polymer and/or styrene-butadiene co-polymer resins in the amount of up to 3%, and/or retarders and/or accelerators of cement binding and hardening process commonly known in the market and/or plasticisers or superplasticisers in the amount from 0.5 to 2% of the cement weight, and/or other additives that modify rheology, especially guar gum ethers in the amount from 0.02 to

0.1%.

[0007] The mortar designed especially for shaped clinker bricks according to the invention retains its physical and chemical properties in full range of values.

[0008] The mortar according to the invention offers much stronger resistance to migration of dissolved salts, as well as lower water absorption, lower absorbability, higher density of hardened mortar, higher compression strength and higher resistance to algae as compared to similar products in the market which was confirmed by tests of absorption, absorbability, ability to migrate the saturated solution of sodium sulphate, density of hardened mortar, and resistance to algae.

[0009] Tests in accordance with PN-EN 1015-18 standard confirmed that mortar constituting the subject of the invention demonstrates the lowest water absorption as compared to mortars available in the market.

[0010] The test that consisted in storing mortars in the w saturated solution of sodium sulphate confirmed that mortar featuring nano-additives constituting the subject of the invention demonstrates a much better resistance to the process of migration of dissolved salt.

[0011] The test that consisted in storing mortars infected with a mixture of green and blue-green algae in conditions favourable for their fast growth confirmed that mortar using biocide constituting the subject of the invention demonstrates resistance to algae.

[0012] Example 1

[0013] To achieve the usable mortar, the following ingredients were used: 18% of Portland cement CEM I 32.5R by weight, 67% of quartz sand of grain size 0.1-1.25 mm by weight, 2% of quartz sand of grain size 0.1-0.2 mm by weight, 10% of limestone flour of grain size of up to 0.5 mm by weight, 3% of quartz flour of grain size of up to 0.25 mm by weight, 0.05% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa.s by weight, 0.5% of redispersible powder on the basis of vinyl acetate co-polymer and ethylene by weight, 0.01% of aerating additive by weight, 1% of ferric pigment by weight, 0.2% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.2% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, 0.18% of biocide by weight, and 14.0% of water in relation to dry mass by weight.

[0014] The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0015] Then, the following tests were conducted:

[0016] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water absorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0017] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending

strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0018] -mortar's ability to block migration of sodium sulphate was also tested

[0019] by our own method. The test consists in storing for the period of 2 months

[0020] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate. The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0021] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0022] According to the example, the following results were achieved:

[0023] water absorption - 0.03 kg/m².min^{1/2}

[0024] compression strength - 13 MPa

[0025] mortar's ability to block migration of sodium sulphate - no salts crystallised inside the mortar, surface of mortar was clear

[0026] resistance of mortar to algae - resistant.

[0027] Example 2

[0028] To achieve the usable mortar, the following ingredients were used: 28% of Portland cement CEM I 32.5R by weight, 64% of quartz sand of grain size 0.1-1.25 mm by weight, 3% of quartz sand of grain size 0.1-0.2 mm by weight, 4% of limestone flour of grain size of up to 0.5 mm by weight, 1% of quartz flour of grain size of up to 0.25 mm by weight, 0.1% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa·s by weight, 0.8% of redispersible powder on the basis of vinyl acetate co-polymer and ethylene by weight, 0.01% of aerating additive by weight, 4% of ferric pigment by weight, 0.1% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.3% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, 0.03% of biocide by weight, and 15.0% of water in relation to dry mass by weight. The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0029] Then, the following tests were conducted:

[0030] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water ab-

sorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0031] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0032] -mortar's ability to block migration of sodium sulphate was also tested

[0033] by our own method. The test consists in storing for the period of 2 months

[0034] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate. The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0035] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0036] According to the example, the following results were achieved:

[0037] water absorption - 0.03 kg/m².min^{1/2}

[0038] compression strength - 17 MPa

[0039] mortar's ability to block migration of sodium sulphate - no salts crystallised inside the mortar, surface of mortar was clear

[0040] resistance of mortar to algae - resistant.

[0041] Example 3

[0042] To achieve the usable mortar, the following ingredients were used: 15% of Portland cement CEM I 32.5R by weight, 59% of quartz sand of grain size 0.1-1.25 mm by weight, 10% of quartz sand of grain size 0.1-0.2 mm by weight, 5% of limestone flour of grain size of up to 0.5 mm by weight, 5% of quartz flour of grain size of up to 0.25 mm by weight, 0.3% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa·s by weight, 1% of redispersible powder on the basis of vinyl acetate co-polymer and ethylene by weight, 0.01% of aerating additive by weight, 0.5% of ferric pigment by weight, 0.5% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.2% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, 0.3% of biocide by weight, 1% of micro-silica by weight, 5% of blast furnace slag by weight, and 18.0% of water in relation to dry mass by weight. The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0043] Then, the following tests were conducted:

[0044] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water absorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0045] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0046] -mortar's ability to block migration of sodium sulphate was also tested

[0047] by our own method. The test consists in storing for the period of 2 months

[0048] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate. The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0049] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0050] According to the example, the following results were achieved:

[0051] water absorption - 0.02 kg/m²·min^{1/2}

[0052] compression strength - 11 MPa

[0053] mortar's ability to block migration of sodium sulphate - no slats crystallised inside the mortar, surface of mortar was clear

[0054] resistance of mortar to algae - resistant.

[0055] Example 4

[0056] To achieve the usable mortar, the following ingredients were used: 28% of Portland cement CEM I 32.5R by weight, 54% of quartz sand of grain size 0.1-1.25 mm by weight, 4% of quartz sand of grain size 0.1-0.2 mm, 7% of limestone flour of grain size of up to 0.5 mm by weight, 7% of quartz flour of grain size of up to 0.25 mm by weight, 0.15% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa·s by weight, 0.5% of redispersible powder on the basis of vinyl acetate co-polymer and ethylene by weight, 0.01% of aerating additive by weight, 3% of ferric pigment by weight, 0.2% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.2% of hydrophobic agent in the form of sil-

icone, powder of nanometric size in capsules in wax envelopes by weight, 0.05% of biocide by weight and 15.0% of water in relation to dry mass by weight. The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0057] Then, the following tests were conducted:

[0058] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water absorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0059] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0060] -mortar's ability to block migration of sodium sulphate was also tested

[0061] by our own method. The test consists in storing for the period of 2 months

[0062] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate. The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0063] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0064] According to the example, the following results were achieved:

[0065] water absorption - 0.02 kg/m²·min^{1/2}

[0066] compression strength - 18 MPa

[0067] mortar's ability to block migration of sodium sulphate - no slats crystallised inside the mortar, surface of mortar was clear

[0068] resistance of mortar to algae - resistant.

[0069] Example 5

[0070] To achieve the usable mortar, the following ingredients were used: 17% of Portland cement CEM I 32.5R by weight, 65% of quartz sand of grain size 0.1-1.25 mm by weight, 7% of quartz sand of grain size 0.1-0.2 mm by weight, 4% of limestone flour of grain size of up to 0.5 mm by weight, 4% of quartz flour of grain size of up to 0.25 mm by weight, 0.05% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa·s by weight, 0.5% of redispersible powder on the basis of vinyl

acetate co-polymer and ethylene by weight, 0.01% of aerating additive by weight, 2% of ferric pigment by weight, 0.05% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.5% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, 0.25% of biocide by weight, 3% by weight of fly-ash, 0.02% by weight of starch ether, 2% of flexibility-improving additive by weight, added in the form of ready resin dispersion of acrylic co-polymer and 17% of water in relation to dry mass by weight. The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0071] Then, the following tests were conducted:

[0072] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water absorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0073] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0074] -mortar's ability to block migration of sodium sulphate was also tested

[0075] by our own method. The test consists in storing for the period of 2 months

[0076] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate. The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0077] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0078] According to the example, the following results were achieved:

[0079] water absorption - 0.02 kg/m²·min^{1/2}

[0080] compression strength - 13 MPa

[0081] mortar's ability to block migration of sodium sulphate - no slats crystallised inside the mortar, surface of mortar was clear

[0082] resistance of mortar to algae - resistant.

[0083] Example 6

[0084] To achieve the usable mortar, the following in-

gredients were used: 20% of Portland cement CEM I 32.5R by weight, 56% of quartz sand of grain size 0.1-1.25 mm by weight, 3% of quartz sand of grain size 0.1-0.2 mm by weight, 8% of limestone flour of grain size of up to 0.5 mm by weight, 2% of quartz flour of grain size of up to 0.25 mm by weight, 0.05% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa·s by weight, 0.5% of redispersible powder on the basis of vinyl acetate co-polymer and ethylene by weight, 0.02% of aerating additive by weight, 0.1% of ferric pigment by weight, 0.2% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.2% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, 0.1% of biocide by weight, 7% by weight of fly-ash, 4% of blast furnace slag by weight, 3% of flexibility-improving additive by weight, added in the form of ready resin dispersion of styrene-butadiene co-polymer, 0.02% of guar gum ether by weight, and 18% of water in relation to dry mass by weight. The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0085] Then, the following tests were conducted:

[0086] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water absorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0087] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0088] -mortar's ability to block migration of sodium sulphate was also tested

[0089] by our own method. The test consists in storing for the period of 2 months

[0090] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate. The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0091] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0092] According to the example, the following results

were achieved:

[0093] water absorption - 0.03 kg/m²·min^{1/2}

[0094] compression strength - 15 MPa

[0095] mortar's ability to block migration of sodium sulphate - no slats crystallised inside the mortar, surface of mortar was clear

[0096] resistance of mortar to algae - resistant.

[0097] Example 7

[0098] To achieve the usable mortar, the following ingredients were used: 18% of Portland cement CEM I 32.5R by weight, 57% of quartz sand of grain size 0.1-1.25 mm by weight, 3% of quartz sand of grain size 0.1-0.2 mm by weight, 7% of limestone flour of grain size of up to 0.5 mm by weight, 3% of quartz flour of grain size of up to 0.25 mm by weight, 0.2% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa·s by weight, 0.5% of redispersible powder on the basis of vinyl acetate co-polymer and ethylene by weight, 0.01% of aerating additive by weight, 1% of ferric pigment by weight, 0.2% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.2% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, 0.15% of biocide by weight, 10% by weight of fly-ash, 2% of blast furnace slag by weight, 0.1% by weight of calcium formate, plasticiser in the amount of 0.5% of the cement weight and 16% of water in relation to dry mass by weight. The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0099] Then, the following tests were conducted:

[0100] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water absorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0101] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0102] -mortar's ability to block migration of sodium sulphate was also tested

[0103] by our own method. The test consists in storing for the period of 2 months

[0104] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate. The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0105] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed

for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0106] According to the example, the following results were achieved:

[0107] water absorption - 0.02 kg/m²·min^{1/2}

[0108] compression strength - 14 MPa

[0109] mortar's ability to block migration of sodium sulphate - no slats crystallised inside the mortar, surface of mortar was clear

[0110] resistance of mortar to algae - resistant.

[0111] Example 8

[0112] To achieve the usable mortar, the following ingredients were used: 17% of Portland cement CEM I 32.5R by weight, 62.5% of quartz sand of grain size 0.1-1.25 mm by weight, 5% of quartz sand of grain size 0.1-0.2 mm by weight, 6% of limestone flour of grain size of up to 0.5 mm by weight, 4% of quartz flour of grain size of up to 0.25 mm by weight, 0.1% of modified methylhydroxyethylcellulose of viscosity of 15000 mPa·s by weight, 0.5% of redispersible powder on the basis of vinyl acetate co-polymer and ethylene by weight, 0.01% of aerating additive by weight, 4% of ferric pigment by weight, 0.3% nanometer-sized additive belongs to the group of silicates, alkaline activated, modified by organic ingredients by weight, 0.2% of hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes by weight, 0.2% of biocide by weight, 5% of micro-silica by weight, 5% of blast furnace slag by weight, 0.05% of guar gum ether by weight, and 17% of water in relation to dry mass by weight. The mortar was prepared for tests in accordance with PN EN-998-2 standard.

[0113] Then, the following tests were conducted:

[0114] -absorption of water, according to PN-EN 1015-18 standard "Methods of Testing Mortars for Walls - Part 18: Determination of water absorption factor caused by capillary raising of hardened mortar". The test consists in measurement of the amount of water absorbed in the given time on the fractures of hardened and stabilised beams of the following dimensions: 4x4x16 cm.

[0115] -compression strength according PN-EN 1015-11 standard "Methods of Testing Mortars for Walls - Part 11: Determination of compression and bending strength of the hardened mortar". The test consists in measurement of compression strength of beams of the following dimensions: 4x4x16 cm with the use of a hydraulic press.

[0116] -mortar's ability to block migration of sodium sulphate was also tested

[0117] by our own method. The test consists in storing for the period of 2 months

[0118] beams of the following dimensions: 4x4x16 cm made of mortar in saturated solution of sodium sulphate.

The test result consists in observation of surfaces and salt migrations through the mortar on the beam broken in half after 2 months.

[0119] -mortar's resistance to algae was also tested. The test consists in storing on the culture medium the properly prepared samples of mortars in the form of rings (stabilised in normal conditions for 48 hours, then rinsed for 2 days so that the sample was in cold water for 8 hours a day) infected with a mixture of green and blue-green algae in the humidity chamber in temperature of 22°C for 12 hours under fluorescent light, and then for 12 hours in darkness each day. The test result consists in observation of the surface of the sample after a week from infection.

[0120] According to the example, the following results were achieved:

[0121] water absorption - 0.02 kg/m².min^{1/2}

[0122] compression strength - 14 MPa

[0123] mortar's ability to block migration of sodium sulphate - no slats crystallised inside the mortar, surface of mortar was clear

[0124] resistance of mortar to algae - resistant.

Claims

1. Mortar especially for shaped clinker bricks comprised of the dry mixture of cement, fillers and chemical additives and requiring addition of water only, **characterised in that** contains from 15 to 28% by weight cement, from 50 to 68% by weight of quartz sand of grain size from 0.1 to 1.25 mm, from 2 to 10% by weight of quartz sand of grain size from 0.1 to 0.2 mm, from 4 to 10% by weight of limestone flour of grain size of up to 0.5 mm, from 1 to 5% by weight of quartz flour of grain size of up to 0.25 mm, modified cellulose ether from 0.05 to 0.3% by weight, redispersible powder from 0.5 to 1.0% by weight, aerating additive in the amount from 0.01 to 0.02% by weight, favourably of organic and non-organic pigments in the amount from 0.1 to 4% by weight, additive of nanometric size favourably belonging to the group of silicates in the amount from 0.05 to 0.5% by weight, hydrophobic agent in the form of silicone, powder of nanometric size in capsules in wax envelopes in the amount from 0.2 to 0.5% by weight, and biocide favourably in the amount from 0.03 to 0.3% by weight.
2. Mortar, according to claim 1, **characterised in that** contains additives of pozzolanic nature especially fly-ash or silica fume or trass flour in the amount from 0.5 to 1.0%, and/or hydraulic additive especially ground, granulated blast furnace slag in the amount from 1.0 to 5.0%, and/or starch ethers in the amount from 0.01 to 0.02%, and/or flexibility-improving additives, especially added in the form of ready resin dispersion of acrylic co-polymer and/or styrene-

butadiene co-polymer resins in the amount of up to 3%, and/or retarders and/or accelerators of cement binding and hardening process commonly known in the market and/or plasticisers or superplasticisers in the amount from 0.5 to 2% of the cement weight, and/or other additives that modify rheology especially guar gum ethers in the amount from 0.02 to 0.1%.

10 Amended claims in accordance with Rule 137(2) EPC.

1. Mortar especially for shaped clinker bricks comprised of the dry mixture of cement, fillers and chemical additives and requiring addition of water only, **characterised in that** contains from 15 to 28% by weight cement, from 50 to 68% by weight of quartz sand of gram size from 0.1 to 1.25 mm, from 2 to 10% by weight of quartz sand of grain size from 0.1 to 0.2 mm, from 4 to 10% by weight of limestone flour of grain size of up to 0.5 mm, from 1 to 5% by weight of quartz flour of grain size of up to 0.25 mm, modified cellulose ether from 0.05 to 0.3% by weight, redispersible powder from 0.5 to 1.0% by weight, aerating additive in the amount from 0.01 to 0.02% by weight, favourably of organic and non-organic pigments in the amount from 0.1 to 4% by weight, additive of nanometric size favourably belonging to the group of silicates in the amount from 0.05 to 0.5% by weight, hydrophobic agent in the form of silicone powder of nanometric size in capsules in wax envelopes in the amount from 0.2 to 0.5% by weight, and biocide favourably in the amount from 0.03 to 0,3% by weight.

2. Mortar, according to claim 1, **characterised in that** contains additives of pozzolanic nature especially fly-ash or silica fume or trass flour in the amount from 0.5 to 1.0%, and/or hydraulic additive especially ground, granulated blast furnace slag in the amount from 1.0 to 5.0%, and/or starch ethers in the amount from 0.01 to 0.02%, and/or flexibility-improving additives, especially added in the form of ready resin dispersion of acrylic co-polymer and/or styrene-butadiene co-polymer resins in the amount of up to 3%, and/or retarders and/or accelerators of cement binding and hardening process commonly known in the market and/or plasticisers or superplasticisers in the amount from 0.5 to 2% of the cement weight, and/or other additives that modify rheology especially guar gum ethers in the amount from 0.02 to 0.1%.

1. Mortar especially for shaped clinker bricks comprised of the dry mixture of cement, fillers and chemical additives and requiring addition of water only, **characterised in that** contains from 15 to 28% by weight cement, from 50 to 68% by weight of quartz sand of gram size from 0.1 to 1.25 mm, from 2 to

10% by weight of quartz sand of grain size from 0.1 to 0.2 mm, from 4 to 10% by weight of limestone flour of grain size of up to 0.5 mm, from 1 to 5% by weight of quartz flour of grain size of up to 0.25 mm, modified cellulose ether from 0.05 to 0.3% by weight, redispersible powder from 0.5 to 1.0% by weight, aerating additive in the amount from 0.01 to 0.02% by weight, favourably of organic and non-organic pigments in the amount from 0.1 to 4% by weight, additive of nanometric size favourably belonging to the group of silicates in the amount from 0.05 to 0.5% by weight, hydrophobic agent in the form of silicone powder of nanometric size in capsules in wax envelopes in the amount from 0.2 to 0.5% by weight, and biocide favourably in the amount from 0.03 to 0.3% by weight.

2. Mortar, according to claim 1, characterised in that contains additives of pozzolanic nature especially fly-ash or silica fume or trass flour in the amount from 0.5 to 1.0%, and/or hydraulic additive especially ground, granulated blast furnace slag in the amount from 1.0 to 5.0%, and/or starch ethers in the amount from 0.01 to 0.02%, and/or flexibility-improving additives, especially added in the form of ready resin dispersion of acrylic co-polymer and/or styrene-butadiene co-polymer resins in the amount of up to 3%, and/or retarders and/or accelerators of cement binding and hardening process commonly known in the market and/or plasticisers or superplasticisers in the amount from 0.5 to 2% of the cement weight, and/or other additives that modify rheology especially guar gum ethers in the amount from 0.02 to 0.1%.

35

40

45

50

55



EUROPEAN SEARCH REPORT

Application Number
EP 09 46 1502

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
A	GB 1 088 485 A (GLIDDEN CO) 25 October 1967 (1967-10-25) * the whole document *	1-2	INV. C04B28/02 C04B28/10
A	----- US 2006/054056 A1 (JUNGK AXEL E [DE]) 16 March 2006 (2006-03-16) * the whole document *	1-2	
A	----- US 5 721 016 A (PANSTER PETER [DE] ET AL) 24 February 1998 (1998-02-24) * the whole document *	1-2	
A	----- US 6 537 366 B1 (SUPPLEE SR WILLIAM W [US]) 25 March 2003 (2003-03-25) * the whole document *	1-2	
			TECHNICAL FIELDS SEARCHED (IPC)
			C04B
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 24 August 2009	Examiner Roesky, Rainer
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03.8Z (F04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 09 46 1502

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-08-2009

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 1088485	A	25-10-1967	NONE	

US 2006054056	A1	16-03-2006	NONE	

US 5721016	A	24-02-1998	NONE	

US 6537366	B1	25-03-2003	NONE	

EPC FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82